

### Features

- Tin-free sustainable film
- High temperature resistance
- Good hydrolysis resistance
- Very good strength and toughness remains even with a thickness of 0.012mm

### Physical Properties

*Properties	Method	Unit	**Value	Note
Thickness		mm	0.015	
Width		mm inch	1524 60	
Color			Translucent	
M.V.T.	ASTM E96-93BW 23°C/50%R.H.	g/m <sup>2</sup> x24hrs	400	
M.V.T.	JIS L1099-1993 A-1(CaCl <sub>2</sub> )40 °C 90% R.H.	g/m <sup>2</sup> x24hrs	1200	
W.P.R.	JIS L1092-1998 B Method	mmH <sub>2</sub> O	10000	
Density	ASTM D792		1.21	
Elongation	ASTM D882	%	470	
Length per kg		Y x 60"/kg	approx. 40Y	
PE Carrier			No	

\*\*Actual results may yield up to ±15%

\*Data provided are used solely for references only, and are not guaranteed statements.