

DING ZING Specification Sheet

Hot Melt Film FS3258X1+DZ03

- Thermoplastic polyurethane
- Heat pressing on seamless pocket/collar/cuff of sleeve
- Heat pressing temperature at 100°C
- Suitable for various laminations
- Eco-friendly

Physical Properties	Unit	Testing Method	Testing Result
Hardness	Shore A/D	ASTM D2240	70A
Specific Gravity	—	ASTM D792	1.16
Tensile Strength	kg/cm ²	ASTM D412	warp: 121 weft: 125
300 % Modulus	kg/cm ²	ASTM D412	warp: 28 weft: 30
Ultimate Elongation	%	ASTM D412	warp: 911 weft: 945
Tear Strength	kg/cm	ASTM D624(Die C)	warp 37 weft 37
Film Melting Point	°C		85



DING ZING CHEMICAL PRODUCTS

SINCE 1981

No. 8-1, Pei-Lin Rd., Hsiao-Kang Dist., Kaohsiung Taiwan, +886-7-8070166,
www.dingzing.com