

Ding Zing® Film FT7078

Features

- Polyurethane polyether base
- Very good low temperature flexibility
- Good hydrolysis resistance
- Easy for processing

Physical Properties

*Properties	Unit	Method	Direction	**Value	Note
Hardness	Shore A	ASTM D2240		78±3	
Specific Gravity		ASTM D792		1.11	
Tensile Strength	Kg/cm ²	ASTM D412	MD CD	338 333	
300% Modulus	Kg/cm ²	ASTM D412	MD CD	85 76	
Elongation	%	ASTM D412	MD CD	669 721	
Tear Strength	Kg/cm	ASTM D624 (Die C)	MD CD	126 126	
Film Melting Point	°C			140	
QUV Discoloration	Grade	ASTM G154 (45°C/24hrs/0.78W/m ²)		4~5	

**Actual results may yield up to ±15%.

*Data provided are used solely for references only, and are not guaranteed statements.



DING ZING CHEMICAL PRODUCTS CO., LTD.

SINCE 1981

http://www.dingzing.com e-mail: film@dingzing.com.tw Tel: +886 - 7 - 8070166
No.8-1, Pei-Lin Rd. Hsiao-Kang Dist., Kaohsiung, Taiwan Fax: +886 - 7 - 8071616