

Features

- Tin-free sustainable film
- High temperature resistance
- Good hydrolysis resistance
- Very good strength and toughness remains even with a thickness of 0.012mm

Physical Properties

| *Properties | Method | Unit | **Value | Note |
|---------------|---|-------------------------|-------------|------|
| Thickness | | mm | 0.012 | |
| Width | | mm inch | 1524 60 | |
| Color | | | Translucent | |
| M.V.T. | ASTM E96-93BW 23°C/50%R.H. | g/m ² x24hrs | 500 | |
| M.V.T. | JIS L1099-1993 A-1(CaCl ₂)40 °C 90% R.H. | g/m ² x24hrs | 1300 | |
| W.P.R. | JIS L1092-1998 B Method | mmH ₂ O | Over 10,000 | |
| Density | ASTM D792 | | 1.21 | |
| Elongation | ASTM D882 | % | 404 | |
| Length per kg | | Y x 60"/kg | approx. 50Y | |
| PE Carrier | | | No | |

**Actual results may yield up to ±15%.

*Data provided are used solely for references only, and are not guaranteed statements.