

Ding Zing® Film FT3070

Features

- Polyurethane polyether base
- With good hydrolysis resistance
- Excellent low temperature flexibility

Physical Properties

*Properties	Unit	Method	Direction	**Value	Note
Hardness	Shore A	ASTM D2240		70 ±3	
Specific Gravity		ASTM D792		1.07	
Tensile Strength	Kg/cm ²	ASTM D412	MD	320	
			CD	272	
Elongation	%	ASTM D412	MD	655	
			CD	802	
300% Modulus	Kg/cm ²	ASTM D412	MD	70	
			CD	46	
Tear Strength	Kg/cm	ASTM D624	MD	90	
			CD	92	
Film Melting Point	°C			140	
UV stability	Grade	ASTM D1148		4	

**Actual results may yield up to ±15%.

*Data provided are used solely for references only, and are not guaranteed statements.



DING ZING CHEMICAL PRODUCTS CO., LTD.

SINCE 1981

http://www.dingzing.com e-mail: film@dingzing.com.tw Tel: +886 - 7 - 8070166
No.8-1, Pei-Lin Rd. Hsiao-Kang Dist., Kaohsiung, Taiwan Fax: +886 - 7 - 8071616