

Ding Zing® Film FT5079

Features

- Polyurethane polyether base
- Softness maintained at low temperature
- High tear strength
- Resistance to aging
- Superior resistance to hydrolysis
- Excellent wear resistance
- Good oil resistance

Physical Properties

*Properties	Unit	Method	Direction	**Value	Note
Hardness	Shore A	ASTM D2240		80±3	
Specific Gravity		ASTM D792		1.11	
Tensile Strength	Kg/cm ²	ASTM D412	MD	320	
			CD	310	
Elongation	%	ASTM D412	MD	615	
			CD	670	
300% Modulus	Kg/cm ²	ASTM D412	MD	70	
			CD	65	
Tear Strength	Kg/cm	ASTM D624	MD	105	
			CD	105	
Film Melting Point	°C			130	
UV stability	Grade	D1148		4~5	

**Actual results may yield up to ±15%.

*Data provided are used solely for references only, and are not guaranteed statements.