

## Ding Zing® Film FS26V0-PE

### Features

- Polyurethane polyester base
- 94V0 grade
- No plasticizer
- Flame retardant hot melt film
- Environmentally friendly
- Suitable for varied laminations

### Physical Properties

| *Properties        | Unit               | Method     | Direction | **Value | Note |
|--------------------|--------------------|------------|-----------|---------|------|
| Hardness           | Shore A            | ASTM D2240 |           | 92 ±3   |      |
| Specific Gravity   |                    | ASTM D792  |           | 1.13    |      |
| Tensile Strength   | Kg/cm <sup>2</sup> | ASTM D882  | MD        | 219     |      |
|                    |                    |            | CD        | 242     |      |
| Elongation         | %                  | ASTM D882  | MD        | 730     |      |
|                    |                    |            | CD        | 769     |      |
| 300% Modulus       | Kg/cm <sup>2</sup> | ASTM D882  | MD        | 69      |      |
|                    |                    |            | CD        | 66      |      |
| Tear Strength      | Kg/cm              | ASTM D624  | MD        | 96      |      |
|                    |                    |            | CD        | 90      |      |
| Film Melting Point | °C                 |            |           | 60      |      |
| UV stability       | Grade              | ASTM D1148 |           | --      |      |

\*\*Actual results may yield up to ±15%.

\*Data provided are used solely for references only, and are not guaranteed statements.