

Ding Zing[®] Film **FS4055-PE**

Features

- Polyurethane polyester base
- Good low temperature flexibility
- Good softness with low hardness
- With remarkable flexibility and excellent recovery

Physical Properties

*Properties	Unit	Method	Direction	**Value	Note
Hardness	Shore A	ASTM D2240		55 ±3	
Specific Gravity		ASTM D792		1.15	
Tensile Strength	Kg/cm ²	ASTM D882	MD	237	
			CD	249	
Elongation	%	ASTM D882	MD	1059	
			CD	1033	
300% Modulus	Kg/cm ²	ASTM D882	MD	25	
			CD	27	
Tear Strength	Kg/cm	ASTM D624	MD	63	
			CD	66	
Film Melting Point	°C			90	
UV stability	Grade	ASTM D1148		--	

**Actual results may yield up to ±15%.

*Data provided are used solely for references only, and are not guaranteed statements.



DING ZING CHEMICAL PRODUCTS CO., LTD.

SINCE 1981

<http://www.dingzing.com> e-mail: film@dingzing.com.tw Tel: +886 - 7 - 8070166
No.8-1, Pei-Lin Rd. Hsiao-Kang Dist., Kaohsiung, Taiwan Fax: +886 - 7 - 8071616