

Ding Zing® Film FS4013

Features

- Polyurethane polyester base
- With hot melt features
- Easy for high frequency welding
- Very good low temperature flexibility

Physical Properties

*Properties	Unit	Method	Direction	**Value	Note
Hardness	Shore A	ASTM D2240		74±3	
Specific Gravity		ASTM D792		1.19	
Tensile Strength	Kg/cm ²	ASTM D412	MD CD	250 210	
300% Modulus	Kg/cm ²	ASTM D412	MD CD	55 45	
Elongation	%	ASTM D412	MD CD	590 580	
Tear Strength	Kg/cm	ASTM D624 (Die C)	MD CD	90 95	
Film Melting Point	°C			115	
QUV Discoloration	Grade	ASTM G154 (45°C/24hrs/0.78W/m ²)		4	

**Actual results may yield up to ±15%.

*Data provided are used solely for references only, and are not guaranteed statements.



DING ZING CHEMICAL PRODUCTS CO., LTD.

SINCE 1981

http://www.dingzing.com e-mail: film@dingzing.com.tw Tel: +886 - 7 - 8070166
No.8-1, Pei-Lin Rd. Hsiao-Kang Dist., Kaohsiung, Taiwan Fax: +886 - 7 - 8071616