

## Ding Zing® Film FT1890

### Features

- Polyurethane polyether base
- Excellent hydrolysis resistance
- Very good low temperature flexibility
- Easy for processing

### Physical Properties

*Properties	Unit	Method	Direction	**Value	Note
Hardness	Shore A	ASTM D2240		90±3	
Specific Gravity		ASTM D792		1.12	
Tensile Strength	Kg/cm <sup>2</sup>	ASTM D412	MD	352	
			CD	348	
Elongation	%	ASTM D412	MD	627	
			CD	620	
300% Modulus	Kg/cm <sup>2</sup>	ASTM D412	MD	117	
			CD	112	
Tear Strength	Kg/cm	ASTM D624	MD	113	
			CD	108	
Film Melting Point	°C			150	
UV stability	Grade	D1148		4	

\*\*Actual results may yield up to ±15%.

\*Data provided are used solely for references only, and are not guaranteed statements.



**DING ZING CHEMICAL PRODUCTS CO., LTD.**

SINCE 1981

<http://www.dingzing.com> e-mail: [film@dingzing.com.tw](mailto:film@dingzing.com.tw) Tel: +886 - 7 - 8070166  
No.8-1, Pei-Lin Rd. Hsiao-Kang Dist., Kaohsiung, Taiwan Fax: +886 - 7 - 8071616