

## Ding Zing® Film FT7078

### Features

- Polyurethane polyether base
- Very good low temperature flexibility
- Good hydrolysis resistance
- Easy for processing

### Physical Properties

*Properties	Unit	Method	Direction	**Value	Note
Hardness	Shore A	ASTM D2240		78±3	
Specific Gravity		ASTM D792		1.11	
Tensile Strength	Kg/cm <sup>2</sup>	ASTM D412	MD	338	
			CD	333	
Elongation	%	ASTM D412	MD	669	
			CD	721	
300% Modulus	Kg/cm <sup>2</sup>	ASTM D412	MD	85	
			CD	76	
Tear Strength	Kg/cm	ASTM D624	MD	126	
			CD	126	
Film Melting Point	°C			140	
UV stability	Grade	D1148		4~5	

\*\*Actual results may yield up to ±15%.

\*Data provided are used solely for references only, and are not guaranteed statements.



**DING ZING CHEMICAL PRODUCTS CO., LTD.**

SINCE 1981

http://www.dingzing.com e-mail: film@dingzing.com.tw Tel: +886 - 7 - 8070166  
No.8-1, Pei-Lin Rd. Hsiao-Kang Dist., Kaohsiung, Taiwan Fax: +886 - 7 - 8071616