

# DING ZING Specification Sheet

## 熱熔膠

FS8080X1+DZ03

- 聚胺酯薄膜(TPU)
- 與運動鞋的網布熱熔接著極佳
- 熔點100°C以上
- 適合多種貼合
- 環保材質

物性	單位	試驗方法	試驗結果
硬度 Hardness	Shore A/D	ASTM D2240	80A
比重 Specific Gravity	—	ASTM D792	1.21
抗張強度 Tensile Strength	kg/cm <sup>2</sup>	ASTM D412	warp: 172 weft: 161
300%模數 300 % Modulus	kg/cm <sup>2</sup>	ASTM D412	warp: 56 weft: 55
伸長率 Ultimate Elongation	%	ASTM D412	warp: 806 weft: 846
撕裂強度 Tear Strength	kg/cm	ASTM D624(Die C)	warp: 71 weft: 73
薄膜熔點 Film Melting Point	°C		115



**DING ZING CHEMICAL PRODUCTS**

SINCE 1981

No. 8-1, Pei-Lin Rd., Hsiao-Kang Dist., Kaohsiung Taiwan, +886-7-8070166,  
www.dingzing.com